



**Swastik Plasticizer**  
Providing Flexibility

## TECHNICAL DATA SHEET

### CP 45%

S.NO.	PARAMETER	TEST METHOD	RESULTS
1.	Colour (HU)	ASTM-D1209	60
2.	Specify Gravity (at 27°C)	ASTM-D1045	1.18
3.	Chlorine Content (%W/W)	ISI 1448-77	45
4.	Viscosity (at 27°C) Poise	Brook Field Viscometer	4
5.	Free Mineral Acidity (mg KOH/gm)	SP/QC/CP-01	0.01
6.	Free Chlorine %	ISI-9189-79	Nil
7.	Volatile Loss (at 180°C/4Hrs) % mm	SP/QC/CP-02	2.2
8.	Heat Stability (at 180°C/30Min)	SP/QC/CP-03	Slight Yellow
9.	Refractive Index (at 27°C)	ASTM-D-1807	1.498
10.	pH Value	SP/QC/CP-05	6.0

**Swastik Plasticizer**  
Providing Flexibility