



Swastik Plasticizer
Providing Flexibility

TECHNICAL DATA SHEET

CP 52%

S.NO.	PARAMETER	TEST METHOD	RESULTS
1.	Colour (HU)	ASTM-D1209	60
2.	Specify Gravity (at 27°C)	ASTM-D1045	1.278
3.	Chlorine Content (%W/W)	ISI 1448-77	52
4.	Viscosity (at 27°C) Poise	Brook Field Viscometer	18
5.	Free Mineral Acidity (mg KOH/gm)	SP/QC/CP-01	0.01
6.	Free Chlorine %	ISI-9189-79	Nil
7.	Volatile Loss (at 180°C/4Hrs) % mm	SP/QC/CP-02	0.7
8.	Heat Stability (at 180°C/30Min)	SP/QC/CP-03	Slight Yellow
9.	Refractive Index (at 27°C)	ASTM-D-1807	1.55
10.	pH Value	SP/QC/CP-05	6.0

Swastik Plasticizer
Providing Flexibility